

Technical Data Sheet**TDS****General Description**

| | |
|----------------|--|
| Product Name | Iron Oxide Brown C686 |
| Type | Brown pigment |
| Chemical Class | Synthetic iron oxide |
| Delivery Form | Powder |
| Color Index | Pigment Red 101, Pigment Yellow 42, Pigment Black 11 |
| CAS | 1309-37-1, 51274-00-1, 1317-61-9 |
| EINECS NO. | 215-168-2, 257-098-5, 215-277-5 |
| Particle Shape | Irregular |

Physical and Chemical properties

| Test Items | Specification |
|---|---------------|
| Appearance | Brown powder |
| Content of Fe ₂ O ₃ , % | 88 min. |
| PH Value | 4-7 |
| Shade | Close to std. |
| Oil Absorption, % | 20-30 |
| Residue on 325 mesh, % | 0.3 max. |
| Water soluble, % | 0.5 max. |
| Volatite at 105°C, % | 1.0 max. |
| Tinting Strength, % | 98-102 |
| DE (compared with std.) | 1 max. |

Application

Recommended for cement products application, such as paving stones, concrete blocks, roofing tiles, bricks, slurry, asphalts, sports racetracks etc..

Package

25kg bag with pallets.

Hangzhou Epsilon Chemical Co.,Ltd.

T.: +86-571-82270817

F.: +86-571-82660715

E: info@epsilonpigments.com

W: <http://www.epsilonpigments.com>